



Europäisches Patentamt  
European Patent Office  
Office européen des brevets



(11) **EP 1 209 203 A1**

(12)

## EUROPEAN PATENT APPLICATION

published in accordance with Art. 158(3) EPC

(43) Date of publication:

29.05.2002 Bulletin 2002/22

(51) Int Cl.7: **C08L 101/00**, C08L 33/12,  
C08F 220/28, C08F 2/38,  
C08F 4/34

(21) Application number: 00915526.8

(22) Date of filing: 14.04.2000

(86) International application number:  
**PCT/JP00/02435**

(87) International publication number:  
**WO 00/64983 (02.11.2000 Gazette 2000/44)**

(84) Designated Contracting States:  
**BE DE ES FR GB IT NL**

(30) Priority: 23.04.1999 JP 11679199  
14.05.1999 JP 13492499

(71) Applicant: **KANEKA CORPORATION**  
Osaka-shi, Osaka 530-8288 (JP)

(72) Inventors:  
• **SUNAGAWA, Takenobu**  
Takasago-shi, Hyogo 676-0812 (JP)

- **NISHIMURA, Riichi**  
Houston, TX 77 000 (US)
- **MORI, Toshiyuki**  
Akashi-shi, Hyogo 673-0844 (JP)
- **TAKAKI, Akira**  
Nada-ku, Kobe-shi, Hyogo 657-0025 (JP)

(74) Representative: **VOSSIUS & PARTNER**  
Siebertstrasse 4  
81675 München (DE)

(54) **PROCESSING AID FOR THERMOPLASTIC RESIN AND THERMOPLASTIC RESIN  
COMPOSITION CONTAINING THE SAME**

(57) The present invention provides a processing aid for thermoplastic resin having a weight average molecular weight of 10,000 to 300,000, which is obtained by polymerizing an alkyl (meth)acrylate, or an alkyl (meth)acrylate and another vinyl monomer copolymer-

izable therewith, in the presence of a mercaptan having an alkyl ester group with C<sub>4-20</sub> alkyl group as a chain transfer agent, and/or an organic peroxide having a tertiary-butyl peroxy group as a polymerization initiator.

## Description

## TECHNICAL FIELD

5 [0001] The present invention relates to a processing aid for thermoplastic resin molding such as calendar molding, blow molding, extrusion molding and injection molding, and a thermoplastic resin composition containing the processing aid, which is excellent in processability, particularly, in peeling property from a metal surface having a high temperature.

## BACKGROUND ART

10 [0002] Thermoplastic resins, such as vinylchloride resins, polyethylene, polypropylene, polyester, polystyrene, polycarbonate, a methacrylate resin, and ABS resin, are excellent in physical properties, and have economic advantage and applicability, and have been widely used in various fields. However, since these resins have high melt viscosity and low fluidity, and are susceptible to thermal decomposition, there are problems in processability that they have a narrow processable condition in molding, and that they tend to stick or adhere to a metal surface of a device in processing at a high temperature.

15 [0003] Now there have been proposed many techniques in order to solve the above-mentioned problems in processability.

20 [0004] Applicability of vinylchloride resins, polyethylene, polypropylene, polyester, polystyrene, polycarbonate, a methacrylate resin, ABS resin and the like can be improved by physically blending modifiers such as a lubricant, a stabilizer, a colorant, a filler, a pigment, a cross-linking agent, a tackifier, a plasticizer, a processing aid, an impact modifier and a modifier for thermal deformation temperature, before processing.

25 [0005] Moreover, in order to improve molding processability at molding of vinylchloride resins, polyethylene, polypropylene, polyester, polystyrene, polycarbonate, a methacrylate resin, and ABS resin, some of copolymers compatible with those resins have been investigated as a processing aid.

30 [0006] For example, there have been proposed a method in which a copolymer of methyl methacrylate and styrene is added to vinylchloride resins (Japanese Examined Patent Publication No. 32-4140 (1957)), a method in which a copolymer of styrene and acrylonitrile is added thereto (Japanese Examined Patent Publication No. 29-5246 (1954)), a method in which a copolymer mainly containing methyl methacrylate is added thereto (Japanese Examined Patent Publication No. 40-5311 (1965)), a method in which a copolymer of styrene and alkyl acrylate is added thereto (Japanese Examined Patent Publication No. 37-1384 (1962)) and the like. Secondary processability such as an increase in melting rate of vinyl chloride resins and an increase in tensile elongation at a high temperature can be improved, but there is no effect in reducing adhesiveness to a metal face of the molding device.

35 [0007] Thereafter, in order to reduce adhesiveness to a metal surface of a molding device, there has been investigated a method in which a copolymer of styrene, an alkyl (meth)acrylate and (meth)acrylate having an oxygen atom in addition to an ester bond is added to vinyl chloride resins (Japanese Examined Patent Publication No. 58-56536 (1983)). In this method the adhesiveness is proved to be improved, but this method cannot always satisfy the demands in the market.

## DISCLOSURE OF THE INVENTION

40 [0008] Taking the above-mentioned circumstances into consideration, it has been found that the above-mentioned problems could be solved by using a polymer as a processing aid, which was obtained by polymerizing a specific amount of monomers having a specific composition and a specific chain transfer agent to complete the present invention. Moreover, it has been found out that the above-mentioned problems could be solved by using a polymer as a processing aid, which was obtained by polymerizing a specific amount of monomers having a specific composition and a specific polymerization initiator to complete the present invention.

45 [0009] Namely, the present invention relates to a processing aid for thermoplastic resin having a weight average molecular weight of 10,000 to 300,000, which is obtained by polymerizing an alkyl (meth)acrylate, or an alkyl (meth) acrylate and another vinyl monomer copolymerizable therewith, in the presence of a mercaptan having an alkyl ester group with 4 to 20 of alkyl carbon as a chain transfer agent, and/or an organic peroxide having a tertiary-butyl peroxy group as a polymerization initiator.

## BEST MODE FOR CARRYING OUT THE INVENTION

55 [0010] The present invention features that a copolymer having a weight average molecular weight of 10,000 to 300,000 is used as a processing aid for thermoplastic resin, which is obtained by polymerizing an alkyl (meth)acrylate, or a monomer mixture comprising an alkyl (meth)acrylate and another vinyl monomer copolymerizable therewith, in

the presence of a mercaptan having an alkyl ester group with 4 to 20 of alkyl carbon as a chain transfer agent, and/or an organic peroxide having a tertiary-butyl peroxy group as a polymerization initiator. More preferably, the present invention features that a copolymer is used as a processing aid for thermoplastic resin, which is obtained by polymerizing a mixture comprising a (meth)acrylate having an oxygen atom in addition to an ester bond, another alkyl acrylate, another vinyl monomer copolymerizable therewith, in the presence of a mercaptan having an alkyl ester group with 4 to 20 of alkyl carbon as an organic peroxide having a tertiary-butylperoxy group as a polymerization initiator.

[0011] By using the copolymer as the processing aid in an amount of 0.1 to 20 parts by weight based on the thermoplastic resin, processability thereof can be improved without losing physical or chemical properties that the resin originally has. Particularly, there arise effects expected by adding the above modifier, such as drastically improving removability from a metal surface at a high temperature.

[0012] The processing aid of the present invention, comprising a copolymer obtained by emulsion polymerizing the above-mentioned monomer mixture, can provide excellent processability, in particular, properties such as a peeling property from a metal surface at a high temperature without degradation in physical and chemical properties of a thermoplastic resin.

[0013] The above-mentioned monomer mixture is a mixture comprising (meth)acrylate having an oxygen atom in addition to an ester bond in an amount of preferably 0.1 to 10 % by weight, more preferably 0.5 to 5 % by weight, and particularly preferably 0.5 to 2 % by weight; another alkyl acrylate in an amount of preferably 10 to 99.9 % by weight, more preferably 10 to 59.5 % by weight, particularly preferably, 10 to 39.5 % by weight; and another vinyl monomer copolymerizable therewith in an amount of preferably 0 to 89.9 % by weight, more preferably 40 to 89.5 % by weight, and particularly preferably 60 to 89.5 % by weight.

[0014] Examples of the (meth)acrylate having an oxygen atom in addition to an ester bond are acrylate containing an epoxy group such as glycidyl acrylate; methacrylate containing an epoxy group such as glycidyl methacrylate; acrylate containing a hydroxy group such as 2-hydroxyethylacrylate and 2-hydroxypropylacrylate; methacrylate containing a hydroxy group such as 2-hydroxyethylmethacrylate and 2-hydroxypropylmethacrylate; acrylate containing an alkoxy group such as methoxyethylacrylate and ethoxyethylacrylate; methacrylate containing an alkoxy group such as methoxyethylmethacrylate and ethoxyethylmethacrylate, and the like. These materials may be used solely or in a combination use of two or more thereof. In order to obtain an excellent peeling property from a metal surface at a high temperature, these materials preferably comprises 0.1 to 10 % by weight. If the content is less than or more than this range, a sufficient peeling effect can not be expected.

[0015] Another alkyl acrylate is preferably an alkyl acrylate containing an alkyl group having 1 to 20 carbon atoms. Examples thereof are those having an alkyl group having 3 to 8 carbon atoms such as 2-ethylhexylacrylate, butylacrylate, and ethylacrylate. These may be used solely or in a combination use of two or more thereof. In order to obtain an excellent peeling property from a metal surface at a high temperature, these materials preferably comprise 10 to 99.9 % by weight thereof. If the content is less or more than this range, a sufficient peeling effect can not be expected.

[0016] Examples of the other vinyl monomer that is copolymerizable with a small amount of (meth)acrylate containing an oxygen atom in addition to an ester bond and the other alkyl acrylate are alkyl methacrylates such as methyl methacrylate and butyl methacrylate, aromatic vinyls such as styrene,  $\alpha$ -methylstyrene and chlorostyrene, acrylonitrile, methacrylonitrile. These may be used solely or in a combination use of two or more thereof. In order to obtain an excellent peeling property from a metal surface at a high temperature, these materials preferably comprises 0 to 89.9 weight %. If the content is less or more than this range, a sufficient peeling effect can not be expected.

[0017] There is no particular limitation for the chain transfer agent. Conventional chain transfer agents, such as tertiary-dodecyl mercaptan, n-dodecyl mercaptan, tertiary-decyl mercaptan and n-decyl mercaptan, may be used depending on demand. An amount of the chain transfer agent is preferably 0.5 to 3 parts by weight based on 100 parts by weight of the monomers in total.

[0018] In particular, a preferable chain transfer agent is a mercaptan containing an alkyl ester group having C<sub>4-20</sub> alkyl group. Examples thereof are tertiary-butylthioglycolate, 2-ethylhexylthioglycolate, 2-ethylhexyl- $\beta$ -mercaptopropionate, and tridecylmercaptopropionate. These may be used solely or in a combination use of two or more thereof. In order to obtain an excellent peeling property from a metal surface at a high temperature, these materials comprise preferably 0.5 to 3 parts by weight based on 100 parts by weight of the monomers in total.

[0019] From the viewpoint of improving the peeling property from a metal surface at a high temperature, a weight average molecular weight of the copolymer comprising the monomer mixture is preferably 10,000 to 300,000.

[0020] There is no particular limitation for the polymerization initiator, but an organic peroxide having a tertiary-butyl peroxy group is preferably used.

[0021] Examples of the organic peroxide having a tertiary-butyl peroxy group are tertiary-butylhydroperoxide, di(tertiary-butyl)peroxyde, tertiary-butyl- $\alpha$ -cumylperoxide, tertiary-butylisopropylcarbonate, tertiary-butylperoxyacetate, tertiary-butylperoxyisobutylate, tertiary-butylperoxyoctanate, tertiary-butylperoxylaurate, tertiary-butylperoxypivalate, tertiary-butylperoxynodecanoate, and tertiary-butylperoxybenzoate. These may be used solely or in a combination use of two or more thereof. In order to obtain an excellent peeling property from a metal surface at a high temperature,

an amount thereof is preferably 0.1 to 5 parts by weight, and more preferably 0.5 to 3 parts by weight.

[0022] The processing aid of the present invention can be prepared by using, for example, the following method. First, the monomer mixture is emulsion polymerized in the presence of a suitable medium, an emulsifier and the chain transfer agent and/or the polymerization initiator. The medium used in the emulsification polymerization is usually water.

[0023] The processing aid of the present invention may be a polymer prepared by single step polymerization or a polymer prepared by a multi-steps polymerization such as two steps or three steps.

[0024] As the emulsifier, there can be used a known emulsifier. Examples thereof are anionic surfactants such as a fatty acid salt, an alkyl sulfate, an alkyl benzene sulfate, an alkyl phosphate, and a diester of sulfosuccinic acid, and non-ionic surfactants such as a polyoxyethylene alkyl ether and a polyoxyethylene fatty acid ester.

[0025] As the above-mentioned chain transfer agent, there can be used the above-mentioned mercaptan having an alkyl ester group with C<sub>4-20</sub> alkyl group.

[0026] As the polymerization initiator, there is usually used a polymerization initiator of the redox type, which contains the above-mentioned organic peroxide having a tertiary-butylperoxy group in combination with a reducing agent. It is possible to use a general organic peroxide in a combination therewith, if necessary.

[0027] There is no particular limitation for a temperature, time and the like at the polymerization condition. Usual temperature and time may be selected, and these may be suitably adjusted to obtain a desired molecular weight and particle size.

[0028] The processing aid of the present invention is mixed with a thermoplastic resin according to a usual method to obtain the thermoplastic resin composition of the present invention.

[0029] An amount at mixing of the thermoplastic resin and the processing aid can be widely set, but the amount thereof is preferably 0.1 to 20 parts by weight, and more preferably 0.5 to 3 parts by weight based on 100 parts by weight of the thermoplastic resin. If the amount is less than 0.1 parts by weight, a sufficient effect can not be obtained. And if the amount is more than 20 parts by weight, transparency of the molded article becomes low and many fish eyes tend to occur.

[0030] The thermoplastic resin includes all normal thermoplastic resins. In particular, there can preferably be vinyl chloride resins, polyethylene, polypropylene, polyester, polystyrene, polycarbonate, a methacrylate resin, ABS resin and the like from the viewpoint of improving the peeling property from a metal surface at a high temperature. Among those, vinyl chloride resins are preferable.

[0031] The vinyl chloride resins are a polymer comprising 80 to 100 % by weight of vinyl chloride unit and 0 to 20 % by weight of another monomer copolymerizable with the vinyl chloride monomer. As the other monomer copolymerizable with the vinyl chloride monomer, examples thereof are vinyl acetate, propylene, styrene, acrylate and the like. These may be used solely or in a combination use of two or more thereof.

[0032] There is no particular limitation for an average polymerization degree and other factors of the vinyl chloride resins, and there may be employed the conventionally used vinyl chloride resins. Examples of the vinyl chloride resins are poly(vinyl chloride), a copolymer of a vinyl chloride monomer of at least 80 % by weight and another copolymerizable monomer, for example, vinyl acetate, propylene, styrene, acrylate, and the like, and chlorinated poly(vinyl chloride). These include homopolymers, and copolymers which contain at least 80 % by weight of vinyl chloride and chlorinated poly(vinyl chloride). These monomers may be used solely or in a combination use of two or more thereof.

[0033] To the vinyl chloride resin composition of the present invention can be suitably added a stabilizer, a lubricant, an impact modifier, a plasticizer, a colorant, a filler and the like at blending, if necessary.

[0034] Example of the above-mentioned polyester is poly(ethylene terephthalate). Moreover, example of the above-mentioned methacrylate resin is poly(methyl methacrylate).

[0035] The thermoplastic resin composition of the present invention is excellent in processability, and they can be molded by a method such as blow molding, injection molding, calendar molding or extrusion molding. The obtained molded article is excellent in appearance properties such as transparency, glow and surface smoothness, as well as in secondary processability, and the resin composition can be suitably applied for various fields such as a film, a sheet, and a profile molded article.

[0036] The present invention is explained in detail by using examples and comparative examples. But the present invention is not intended to be limited thereby. Hereinafter, "parts" represents "parts by weight" based on 100 parts by weight of the monomers in total, unless otherwise specified. In examples and comparative examples, BA represents butyl acrylate, EA represents ethyl acrylate, 2EHA represents 2-ethylhexyl acrylate, St represents styrene, MMA represents methyl methacrylate, AN represents acrylonitrile, GMA represents glycidyl methacrylate, 2HEMA represents 2-hydroxyethyl methacrylate, 2EHTG represents 2-ethylhexyl thioglycolate, ETOM represents ethoxyethyl methacrylate, GA represents glycidyl acrylate, 2HEA represents 2-hydroxyethyl acrylate, ETOA represents ethoxyethyl acrylate, TBHP represents tertiary-butylhydroperoxide.

[0037] The following description shows an evaluation method applied to examples and comparative examples.

(Polymerization conversion)

**[0038]** Polymerization conversion was calculated based on the following equation:

$$\text{Polymerization conversion (\%)} = (\text{Amount of produced polymer} / \text{Amount of loaded monomer}) \times 100(\%)$$

(Roll peeling property)

**[0039]** In order to evaluate the roll peeling property, there was kneaded a mixture comprising 100 parts of poly(vinyl chloride) (Kane vinyl S1007 available from Kaneka Corp.), 1 part of a processing aid, 2.0 parts of a stabilizer of octyl tin mercaptan (TVS #8831 available from Nitto Kasei K.K.), 1.0 part of a lubricant (KALCOHL 8668 available from Kao Corp.), and 3.0 parts of dioctyl phthalate (DOP) by using a 6-inch roll at 190°C, to evaluate peeling property from the roll surface after 10 minutes. The evaluation was made in accordance with ten ranks. Based upon the following criteria, 10 was evaluated as the highest peeling property, and 1 was evaluated as the lowest.

**[0040]** 10: A molten sheet maintains a state removable from a hot roll surface for 10 minutes or more.

**[0041]** 5: A molten sheet maintains a state removable from a hot roll surface for at least 5 minutes to less than 6 minute.

**[0042]** 1: A molten sheet is maintained removable from a hot roll surface for 2 minutes or less.

(Transparency)

**[0043]** In order to evaluate transparency, after the composition was kneaded for 5 minutes at 170°C by using an 8-inch roll, it was then pressed for 15 minutes at 180°C to prepare a plaque having a thickness of 3 mm. Light transmittance for all light rays and haze of the plaque were measured by using an integral bulb-type light-ray transmittance measuring device according to JIS-6714 standard. It shows that the larger the value of the transmittance is, the better the transparency becomes, and the smaller the value of the haze, the better the transparency becomes.

#### EXAMPLE 1

**[0044]** A reactor equipped with a stirrer and a condenser was charged with 200 parts of distilled water, 1.2 parts of sodium dioctylsulfosuccinate, 0.01 part of sodium ethylenediaminetetraacetate, 0.005 part of ferrous sulfate heptahydrate, and 0.5 parts of sodium formaldehyde hydrosulfite. Then, after inside of the reactor was replaced by nitrogen, the reactor was heated to 60°C with stirring. Next, to this was continuously added for two hours a mixture comprising 30 % by weight of methyl methacrylate (MMA), 19 % by weight of styrene (St) and 0.2 part of tertiary-butyl hydroperoxide (TBHP). One hour after completion of the addition, to this was further continuously added for three hours a mixture comprising 35 % by weight of St, 15 % by weight of butyl acrylate (BA), 1.0 % by weight of glycidyl methacrylate (GMA), 1.0 part of 2-ethylhexyl thioglycolate (2 EHTG) and 0.8 parts of TBHP. After completion of the addition, the mixture was further stirred for one hour, and then cooled to obtain a copolymer in latex. Polymerization conversion was 99.4 %.

**[0045]** The obtained latex was coagulated with an aqueous solution of calcium chloride. After the latex was treated up to 90°C, the latex was filtrated with a centrifugal dehydrator. The obtained dehydrated cake of the copolymer was washed with water and dried for 15 hours at 50°C with a parallel-flow dryer to obtain a white powdery sample (1) prepared by two steps polymerization. A weight average molecular weight of the obtained sample was 70,000 measured by GPC. The obtained sample was subjected to the above-mentioned evaluation on the roll peeling property. Table 1 shows the results.

#### EXAMPLES 2 to 7 and COMPARATIVE EXAMPLES 1 to 3

**[0046]** According to compositions shown in Table 1, samples (2) to (10) were obtained by the same manner as in Example 1. The obtained samples were subjected to the above-mentioned evaluation on the roll peeling property. Table 1 shows the results.

**[0047]** From the results shown in Table 1, as indicated by samples (1) and (4) to (9), it is found that a composition having an excellent roll peeling property is obtained when a composition of the monomer mixture is in the range of the present invention. On the other hand, there is a reduction in the roll peeling property when the composition is out of the range of the present invention, that is, in the case of samples (2), (3) and (10).

TABLE 1

Example No.	Sample	Composition of mixture before polymerization (% by weight)										Chain transfer agent (parts)	Organic peroxide (parts)	Roll peeling property	Weight average molecular weight
		Polymer at first step					Polymer at second step								
		MMA	AN	St	BA	EA	2EHA	St	GMA	2EHG	TBHP				
Ex 1	(1)	30		19	15			35	1.0	1.0	1.0			10	70,000
Com. Ex 1	(2)	30		20	15			35	0	1.0	1.0			4	80,000
Com. Ex 2	(3)	26		18	13			31	12	1.0	1.0			4	70,000
Ex 2	(4)	6		4	80			6	1.0	1.0	1.0			9	80,000
Ex 3	(5)	30		19	11			39	1.0	1.0	1.0			9	70,000
Ex 4	(6)	30		19		15		35	1.0	1.0	1.0			9	70,000
Ex 5	(7)	30		19			15	35	1.0	1.0	1.0			9	70,000
Ex 6	(8)		30	19	15			35	1.0	1.0	1.0			9	80,000
Ex 7	(9)	49			50				1.0	1.0	1.0			8	70,000
Com. Ex 3	(10)	30		19	9			41	1.0	1.0	1.0			3	70,000

## EXAMPLE 8

[0048] A reactor equipped with a stirrer and a condenser was charged with 200 parts of distilled water, 1.2 parts of sodium dioctylsulfosuccinate, 0.01 part of sodium ethylenediaminetetraacetate, 0.005 part of ferrous sulfate heptahydrate, and 0.5 part of sodium formaldehyde hydrosulfite. Then, after inside of the reactor was replaced with nitrogen gas, the reactor was heated to 60°C with stirring. Next, to this was continuously added for two hours a mixture comprising 24 % by weight of MMA, 15 % by weight of St and 0.2 part of TBHP. One hour after completion of the addition, to this was further continuously added for three hours a mixture comprising 35 % by weight of St, 15 % by weight of BA, 1.0 % by weight of GMA, 1.0 part of 2EHTG and 0.7 part of TBHP. One hour after completion of the addition, to this was further continuously added for thirty minutes a mixture comprising 10 % by weight of MMA and 0.1 part of TBHP. After completion of the addition, this was further stirred for one hour, and then cooled to obtain a copolymer in latex.

[0049] Polymerization conversion was 99.5 %. The obtained latex was coagulated by an aqueous solution of calcium chloride. After the latex was heated up to 90°C, the latex was filtrated with a centrifugal dehydrator. The obtained dehydrated cake of the copolymer was washed with water and dried for 15 hours at 50°C with a parallel-flow dryer to obtain a white powdery polymer sample (11) prepared by three steps polymerization. A weight average molecular weight of the obtained sample was 80,000 measured by GPC. The obtained sample was subjected to the above-mentioned evaluation on the roll peeling property. Table 2 shows the results.

EXAMPLES 9 to 14 and COMPARATIVE EXAMPLES 4 to 6

[0050] According to compositions shown in Table 2, samples (12) to (20) were obtained by the same manner as in Example 8. The obtained samples were subjected to the above-mentioned evaluation on the roll peeling property. Table 2 shows the results.

[0051] As indicated by samples (11) and (14) to (19), from the results shown in Table 2, it is found that a composition having an excellent roll peeling property is obtained when the composition of the monomer mixture is in the range of the present invention. On the other hand, there is a reduction in the roll peeling property when the composition is out of the range of the present invention, that is, in the case of samples (12), (13) and (20).

TABLE 2

Example No.	Sample	Composition of mixture before polymerization (% by weight)											Chain transfer agent (parts)	Organic peroxide (parts)	Roll peeling property	Weight average molecular weight		
		Polymer at first step		Polymer at second step				Polymer at third step			GMA	MMA					AN	
		MMA	AN	St	BA	EA	2EHA	St	GMA	MMA								AN
Ex. 8	(11)	24		15	15			35	1.0	10		1.0	1.0	10	80,000			
Com. Ex. 4	(12)	24		16	15			35	0	10		1.0	1.0	4	80,000			
Com. Ex. 5	(13)	21		14	13			31	12	9		1.0	1.0	4	90,000			
Ex. 9	(14)	6		4	83			6	1.0	3		1.0	1.0	9	80,000			
Ex. 10	(15)	23		15	11			39	1.0	12		1.0	1.0	9	80,000			
Ex. 11	(16)	24		15		15		35	1.0	10		1.0	1.0	9	80,000			
Ex. 12	(17)	24		15			15	35	1.0	10		1.0	1.0	9	80,000			
Ex. 13	(18)		24	15	15			35	1.0		10	1.0	1.0	9	90,000			
Ex. 14	(19)	39			50				1.0	10		1.0	1.0	8	80,000			
Com. Ex. 6	(20)	24		15	9			41	1.0	10		1.0	1.0	3	80,000			



## EXAMPLES 15 to 22

[0052] The samples (21) to (28) were obtained by setting all the monomers except the amount of GMA used in Example 8 was charged to 100 parts, and adding respective monomers in amounts (parts) shown in Table 3 in the same manner as in Example 8. The obtained samples were subjected to the above-mentioned evaluation on the roll peeling property. Table 3 shows the results.

[0053] As indicated by samples (11) and (21) to (28), from the results shown in Table 3, it is found that a composition having an excellent roll peeling property is obtained when the kind and amount of (meth)acrylate having oxygen atoms in addition to an ester bond are in the range of the present invention.

TABLE 3

Example No.	Sample	Monomer		Roll peeling property	Weight average molecular weight
		Kind	Amount (parts)		
Ex. 8	(11)	GMA	1.0	10	80,000
Ex. 15	(21)	2HEMA	1.0	10	90,000
Ex. 16	(22)	ETOMA	1.0	10	80,000
Ex. 17	(23)	GA	1.0	10	80,000
Ex. 18	(24)	2HEA	1.0	10	80,000
Ex. 19	(25)	ETOA	1.0	10	90,000
Ex. 20	(26)	{ GMA 2HEA	{ 0.5 0.5	10	80,000
Ex. 21	(27)	GMA	0.3	8	80,000
Ex. 22	(28)	GMA	3.0	9	80,000
Com. Ex. 4	(12)	GMA	0	4	80,000
Com. Ex. 5	(13)	GMA	12	4	90,000

## EXAMPLES 23 to 26 and COMPARATIVE EXAMPLES 7 to 11

[0054] The samples (29) to (37) were obtained in the same manner as in Example 8 except that 1.0 part of 2EHTG was replaced by compounds shown in Table 4. The obtained samples were subjected to the above-mentioned evaluation on the roll peeling property. Table 4 shows the results.

[0055] As indicated by samples (11), (29), (30), (32) and (33), from the results shown in Table 4, it is found that a composition having an excellent roll peeling property can be obtained when the particular chain transfer agent is used in an amount of the present invention. On the other hand, roll peeling property becomes low when the particular chain transfer agent is not used or an amount of the chain transfer agent is out of the range of the present invention, that is, in the case of samples (31) and (34) to (37).

TABLE 4

Example No.	Sample	Chain transfer agent		Roll peeling property	Weight average molecular weight
		Kind	Amount (parts)		
Ex. 8	(11)	2EHTG	1.0	10	80,000
Ex. 23	(29)	2EHTG	0.5	9	130,000
Ex. 24	(30)	2EHTG	3.0	9	60,000
Com. Ex. 7	(31)	2EHTG	0	4	210,000
Ex. 25	(32)	2-ethylhexyl- $\beta$ -mercaptopropionate	1.0	10	80,000
Ex. 26	(33)	2EHTG	0.5	10	80,000
		{ 2-ethylhexyl- $\beta$ -mercaptopropionate	0.5		
Com. Ex. 8	(34)	tert-dodecyl mercaptane	1.0	5	80,000
Com. Ex. 9	(35)	n-dodecyl mercaptane	1.0	5	80,000
Com. Ex. 10	(36)	n-octyl mercaptane	1.0	5	80,000
Com. Ex. 11	(37)	thioglycolic acid	1.0	4	80,000

EXAMPLES 27 to 29 and COMPARATIVE EXAMPLES 12 to 15

[0056] The samples (38) to (44) were obtained in the same manner as in Example 8 except that 1.0 part of TBHP

was replaced by compounds shown in Table 5. The obtained samples were subjected to the above-mentioned evaluation on the roll peeling property. Table 5 shows the results.

**[0057]** As indicated by samples (11), (38) to (40), from the results shown in Table 5, it is found that a composition having an excellent roll peeling property is obtained when the particular organic peroxide having a tertiary butylperoxy group is used in an amount of the present invention.

**[0058]** On the other hand, the roll peeling property becomes low, when the particular organic peroxide having a tertiary-butylperoxy group is not used or an amount thereof is out of the range of the present invention, that is, in the case of samples (41) to (44).

TABLE 5

Example No.	Sample	Organic peroxide		Roll peeling property	Weight average molecular weight
		Kind	Amount (parts)		
Ex. 8	(11)	TBHP	1.0	10	80,000
Ex. 27	(38)	TBHP	0.3	9	180,000
Ex. 28	(39)	di-tert-butyl peroxide	1.0	10	80,000
Ex. 29	(40)	{ TBHP	0.5	10	80,000
		{ di-tert-butyl peroxide	0.5		
Com. Ex. 12	(41)	paramentane hydroperoxide	1.0	6	80,000
Com. Ex. 13	(42)	cumene hydroperoxide	1.0	5	80,000
Com. Ex. 14	(43)	benzoyl peroxide	1.0	5	80,000
Com. Ex. 15	(44)	{ TBHP	0.05	6	80,000
		{ cumene hydroperoxide	1.0		

EXAMPLES 30 to 32 and COMPARATIVE EXAMPLES 16 and 17

[0059] Sample (11) obtained in Example 8 was blended with vinyl chloride resin and additives at the ratios shown in Table 6, and the obtained samples were subjected to the transparency evaluation and the evaluation on the roll peeling property. Table 6 shows the results.

[0060] From the results shown in Table 6, it is found that a composition having an excellent roll peeling property is obtained when the amounts of addition are in the range of the present invention.

TABLE 6

Example No.	Poly(vinyl chloride) (parts)	Polymer (11) (parts)	Stabilizer (parts)	Lubricant (parts)	DOP (parts)	Transparency		Roll peeling property
						Transmittance (%)	Haze (%)	
Ex. 30	100	1.0	20	1.0	30	84.2	20.8	10
Ex. 31	100	0.3	20	1.0	30	84.8	20.8	7
Ex. 32	100	15	20	1.0	30	80.8	21.2	8
Com. Ex. 16	100	0	20	1.0	30	86.0	20.6	1
Com. Ex. 17	100	25	20	1.0	30	73.7	28.1	3

EXAMPLES 33 to 40 and COMPARATIVE EXAMPLES 18 to 25

[0061] Sample (11) obtained in Example 8 was blended with a thermoplastic resin and a mixture of poly(vinyl chloride) and another thermoplastic resin at the ratios shown in Table 7, and the obtained samples were subjected to the above-mentioned evaluation on the roll peeling property. Table 7 shows the results.

[0062] From the results shown in Table 7, it is found that an excellent roll peeling property is obtained, when the amounts of addition are in the range of the present invention. In Examples 30, 33, 40 and Comparative Examples 16, 18 and 25, there were added 2.0 parts of octyl tin mercaptan based stabilizer (TVS #8831 available from Nitto Kasei K.K.), 1.0 part of a lubricant (KALCOHL 8668 available from Kao Corp.), and 3.0 parts of DOP thereto.

[0063] In the Table, PVC represents poly(vinyl chloride), CPVC represents chlorinated poly(vinyl chloride), PP represents polypropylene, PET represents poly(ethylene terephthalate), PC represents polycarbonate, PS represents polystyrene, PMMA represents poly(methyl methacrylate) and ABS represents an ABS resin.

TABLE 7

Example No.	Poly(vinyl chloride) resins (parts)		Thermoplastic resin (parts)							Polymer (11) (parts)	Roll peeling property
	PVC	CPVC	PP	PET	PC	PS	PMMA	ABS			
Ex. 30	100									1.0	10
Ex. 33		100								1.0	9
Ex. 34			100							1.0	9
Ex. 35				100						1.0	9
Ex. 36					100					1.0	9
Ex. 37						100				1.0	9
Ex. 38							100			1.0	9
Ex. 39								100		1.0	10
Ex. 40	70							30		1.0	10
Com. Ex. 16	100									0	1
Com. Ex. 18		100								0	1
Com. Ex. 19			100							0	1
Com. Ex. 20				100						0	1
Com. Ex. 21					100					0	1
Com. Ex. 22						100				0	1
Com. Ex. 23							100			0	1
Com. Ex. 24								100		0	1
Com. Ex. 25	70							30		0	1

## EXAMPLE 41

[0064] The sample (45) was obtained in the same manner as in Example 1 except that 1.0 part of 2EHTG was replaced by 1.0 part of tertiary-dodecyl mercaptan (TDM). Polymerization conversion was 99.6 %. A weight average

molecular weight of the obtained sample was 70,000 measured by GPC.

[0065] The obtained sample was subjected to the above-mentioned evaluation on the roll peeling property. Table 8 shows the results.

5      EXAMPLES 42 to 49 and COMPARATIVE EXAMPLES 26 to 29

[0066] According to compositions shown in Table 8, samples (46) to (57) were obtained in the same manner as in Example 41.

10      [0067] The obtained samples were subjected to the above-mentioned evaluation of the roll peeling property. Table 8 shows the results.

[0068] As indicated by samples (45) to (47) and (51) to (56), from the results shown in Table 8, it is found that a composition having an excellent roll peeling property is obtained when the composition of the monomer mixture is in the range of the present invention. On the other hand, when the composition is out of the range of the present invention, that is, in the case of samples (48) to (50) and (57), there is a decline of the roll peeling property.

15

20

25

30

35

40

45

50

55



TABLE 8

Example No.	Sample	Composition of mixture before polymerization (% by weight)										Chain transfer agent (parts)	Organic peroxide (parts)	Roll peeling property	Weight average molecular weight
		Polymer at first step					Polymer at second step								
		MMA	AN	St	BA	EA	2EHA	St	GMA	TDM	TBHP				
Ex 41	(45)	30		19	15			35	10	1.0	1.0			10	70,000
Ex 42	(46)	30		19	15			35	10	0.2	1.0			9	150,000
Ex 43	(47)	30		19	15			35	10	0	1.0			7	210,000
Com. Ex 26	(48)	30		20	15			35	0	1.0	1.0			4	70,000
Com. Ex 27	(49)	30		20	15			35	0	0	1.0			3	210,000
Com. Ex 28	(50)	26		18	13			31	12	1.0	1.0			4	70,000
Ex 44	(51)	6		4	83			6	10	1.0	1.0			8	70,000
Ex 45	(52)	30		19	11			39	10	1.0	1.0			8	70,000
Ex 46	(53)	30		19		15		35	10	1.0	1.0			8	70,000
Ex 47	(54)	30		19			15	35	10	1.0	1.0			8	80,000
Ex 48	(55)		30	19				35	10	1.0	1.0			8	80,000
Ex 49	(56)	49			50				10	1.0	1.0			8	80,000
Com. Ex 29	(57)	30		19	8			42	10	1.0	1.0			2	70,000

EXAMPLE 50

[0069] The same manner as in Example 1 was used except that 1.0 part of 2EHTG was replaced by 1.0 part of TDM to obtain sample (58). The polymerization conversion was 99.7 %. The weight average molecular weight of the resulting sample was measured by GPC, thereby obtaining 90,000.

[0070] The resulting sample was subjected to the above-mentioned evaluation on the roll peeling property. Table 9 shows the results of evaluation.

EXAMPLES 51 to 58 and COMPARATIVE EXAMPLES 30 to 33

[0071] According to compositions shown in Table 9, samples (59) to (70) were obtained in the same manner as in Example 50. The obtained samples were subjected to the above-mentioned evaluation on the roll peeling property. Table 9 shows the results.

[0072] As indicated by samples (58) to (60) and (64) to (69), from the results shown in Table 9, it is found that a composition having an excellent roll peeling property is obtained when the composition of the monomer mixture is in the range of the present invention. On the other hand, when the composition is out of the range of the present invention, that is, in the case of samples (61) to (63) and (70), there is a decline of the roll peeling property.

TABLE 9

Example No.	Sample	Composition of mixture before polymerization (% by weight)												Chain transfer agent (parts)	Organic peroxide (parts)	Roll peeling property	Weight average molecular weight
		Polymer at first step			Polymer at second step						Polymer at third step						
		MMA	AN	St	BA	EA	ZEHA	St	CMA	MMA	AN	AN					
Ex50	(59)	24		15	15		35	10		10		10	10	10	90,000		
Ex51	(60)	24		15	15		35	10		10		0.2	1.0	9	150,000		
Ex52	(61)	24		15	15		35	10		10		0	1.0	7	200,000		
OmEx30	(62)	24		16	15		35	0		10		1.0	1.0	4	90,000		
OmEx31	(63)	24		16	15		35	0		10		0	1.0	3	210,000		
OmEx32	(64)	21		14	13		31	12		9		1.0	1.0	4	80,000		
Ex53	(65)	6		4	83		6	10		3		1.0	1.0	8	80,000		
Ex54	(66)	23		15	11		39	10		12		1.0	1.0	9	90,000		
Ex55	(67)	24		15			35	10	15	10		1.0	1.0	8	90,000		
Ex56	(68)	24		15			35	10		10		1.0	1.0	8	80,000		
Ex57	(69)		24	15			35	10		10		1.0	1.0	8	90,000		
Ex58	(70)	39			50			10		10		1.0	1.0	8	80,000		
OmEx33	(71)	24		15	8		42	10		10		1.0	1.0	2	80,000		

## EXAMPLES 59 to 66

[0073] Samples (71) to (78) were obtained in the same manner as in Example 50, by setting all monomers except GMA used in Example 50 to 100 parts by weight, and using respective monomers shown in Table 3 in the respective blending amounts (parts by weight). The obtained samples were subjected to the above-mentioned evaluation of the roll peeling property. Table 10 shows the results.

[0074] As indicated by samples (58) and (71) to (78), from the results shown in Table 9, it is found that a composition having an excellent roll peeling property is obtained when the (meth)acrylate having an oxygen atom in addition to an ester bond is used in an amount of the present invention.

TABLE 10

Example No.	Sample	Monomer		Roll peeling property	Weight average molecular weight
		Kind	Amount (parts)		
Ex. 50	(58)	GMA	1.0	10	90,000
Ex. 59	(71)	2HEMA	1.0	10	80,000
Ex. 60	(72)	ETOMA	1.0	10	80,000
Ex. 61	(73)	GA	1.0	10	80,000
Ex. 62	(74)	2HEA	1.0	10	80,000
Ex. 63	(75)	ETOA	1.0	10	90,000
Ex. 64	(76)	{ GMA 2HEA	{ 0.5 0.5	10	90,000
Ex. 65	(77)	GMA	0.3	8	80,000
Ex. 66	(78)	GMA	3.0	9	80,000
Com. Ex. 30	(61)	GMA	0	4	90,000
Com. Ex. 32	(63)	GMA	12	4	80,000

## EXAMPLES 67 to 69 and COMPARATIVE EXAMPLES 34 to 37

[0075] The samples (79) to (85) were obtained in the same manner as in Example 50 except that 1.0 part of TBHP was replaced by a polymerization initiator shown in Table 11. The obtained samples were subjected to the above-mentioned evaluation on the roll peeling property. Table 11 shows the results.

[0076] As indicated by samples (79) to (81), from the results shown in Table 11, it is found that a composition having an excellent roll peeling property is obtained when the particular polymerization initiator is used in an amount of the present invention. On the other hand, when the particular polymerization initiator is not used and an amount thereof is out of the range of the present invention, that is, in the case of samples (82) to (85), there is a reduction in the roll peeling property.

TABLE 11

Example No.	Sample	Organic peroxide		Roll peeling property	Weight average molecular property
		Kind	Amount (parts)		
Ex. 50	(58)	TBHP	1.0	10	90,000
Ex. 67	(79)	TBHP	0.3	9	150,000
Ex. 68	(80)	di-tert-butyl peroxide	1.0	10	80,000
Ex. 69	(81)	TBHP	0.5	10	90,000
		di-tert-butyl peroxide	0.5		
Com. Ex. 34	(82)	paramentane hydroperoxide	1.0	3	80,000
Com. Ex. 35	(83)	cumene hydroperoxide	1.0	3	90,000
Com. Ex. 36	(84)	benzoyl peroxide	1.0	3	90,000
Com. Ex. 37	(85)	TBHP	0.05	3	90,000
		cumene hydroperoxide	1.0		

EXAMPLES 70 to 72 and COMPARATIVE EXAMPLES 38 and 39

[0077] Sample (58) obtained in Example 50 was blended with a vinyl chloride resin and additives at the ratios shown in Table 12. The obtained samples were subjected to the evaluation on the transparency and roll peeling property. Table 12 shows the results.

[0078] From the results shown in Table 12, it is found that a composition having an excellent roll peeling property is obtained when the amounts of addition are in the range of the present invention.

TABLE 12

Example No.	Poly(vinyl chloride) (parts)	Polymer (58) (parts)	Stabilizer (parts)	Lubricant (parts)	DOP (parts)	Transparency		Roll peeling property
						Transmittance (%)	Haze (%)	
Ex. 70	100	1.0	2.0	1.0	3.0	84.0	21.0	10
Ex. 71	100	0.3	2.0	1.0	3.0	85.4	20.9	7
Ex. 72	100	15	2.0	1.0	3.0	81.3	21.3	9
Com. Ex. 38	100	0	2.0	1.0	3.0	86.0	20.7	1
Com. Ex. 39	100	25	2.0	1.0	3.0	72.4	29.8	4

EXAMPLES 73 to 80 and COMPARATIVE EXAMPLES 40 to 47

**[0079]** Sample (58) obtained in Example 50 was blended with a thermoplastic resin and a mixture of poly(vinyl chloride) and another thermoplastic resin at the ratios shown in Table 13, and the obtained samples were subjected to the evaluation on the roll peeling property. Table 13 shows the results.

**[0080]** From the results shown in Table 13, it is found that a composition having an excellent roll peeling property is obtained when the amounts of addition are in the range of the present invention. In Examples 70, 73, 80 and Comparative Examples 38, 40 and 47, there were added 2.0 parts of octyl tin mercaptan based stabilizer (TVS #8831 available from Nitto Kasei K.K.), 1.0 part of a lubricant (KALCOHL 8668 available from Kao Corp.), and 3.0 parts of DOP thereto.

TABLE 13

TABLE 13

Example No.	Poly(vinyl chloride) resins (parts)		Thermoplastic resin (parts)							Polymer (58) (parts)	Roll peeling property
	PVC	CPVC	PP	PET	PC	PS	PMMA	ABS			
Ex. 70	100								1.0	10	
Ex. 73		100							1.0	9	
Ex. 74			100						1.0	9	
Ex. 75				100					1.0	9	
Ex. 76					100				1.0	9	
Ex. 77						100			1.0	9	
Ex. 78							100		1.0	9	
Ex. 79								100	1.0	10	
Ex. 80	70							30	1.0	10	
Com. Ex. 38	100								0	1	
Com. Ex. 39		100							0	1	
Com. Ex. 40			100						0	1	
Com. Ex. 41				100					0	1	
Com. Ex. 42					100				0	1	
Com. Ex. 43						100			0	1	
Com. Ex. 44							100		0	1	
Com. Ex. 45								100	0	1	
Com. Ex. 46	70								0	1	
								30	0	1	

## INDUSTRIAL APPLICABILITY

[0081] A thermoplastic resin composition containing the processing aid for thermoplastic resin of the present inven-



tion is excellent in peeling property from a metal surface at a high temperature as compared with conventional resins, and provides a longer processable time.

## 5 Claims

1. A processing aid for thermoplastic resin having a weight average molecular weight of 10,000 to 300,000, which is obtained by polymerizing an alkyl (meth)acrylate, or an alkyl (meth)acrylate and another vinyl monomer copolymerizable therewith, in the presence of a mercaptan having an alkyl ester group with C<sub>4-20</sub> alkyl group as a chain transfer agent, and/or an organic peroxide having a tertiary-butyl peroxy group as a polymerization initiator.
2. The processing aid for thermoplastic resin of Claim 1, which is obtained by polymerizing 0.1 to 10 % by weight of the (meth)acrylate having an oxygen atom in addition to an ester bond as said alkyl (meth)acrylate, 10 to 99.9 % by weight of another alkyl acrylate, and 0 to 89.9 % by weight of another vinyl monomer copolymerizable therewith.
3. The processing aid for thermoplastic resin of Claim 1, wherein an amount of the organic peroxide having a tertiary-butyl peroxy group is 0.1 to 5 parts by weight based on 100 parts by weight of the entire monomers.
4. A thermoplastic resin composition comprising 100 parts by weight of a thermoplastic resin and 0.1 to 20 parts by weight of the processing aid for thermoplastic resin of Claim 1.
5. The thermoplastic resin composition of Claim 4, wherein the thermoplastic resin is at least one resin selected from the group consisting of poly(vinyl chloride) resins, polyethylene, polypropylene, polyester, polystyrene, polycarbonate, a methacrylate resin and an ABS resin.
6. The processing aid for thermoplastic resin of Claim 2, wherein the (meth)acrylate having an oxygen atom in addition to an ester bond is a (meth)acrylate containing an epoxy group.
7. The processing aid for thermoplastic resin of Claim 2, wherein the (meth)acrylate having an oxygen atom in addition to an ester bond is a (meth)acrylate containing a hydroxy group.
8. The processing aid for thermoplastic resin of Claim 2, wherein the (meth)acrylate having an oxygen atom in addition to an ester bond is a (meth)acrylate containing an alkoxy group.

## INTERNATIONAL SEARCH REPORT

International application No.

PCT/JP00/02435

<b>A. CLASSIFICATION OF SUBJECT MATTER</b> Int.Cl <sup>7</sup> C08L101/00, C08L33/12, C08F220/28, C08F2/38, C08F4/34 According to International Patent Classification (IPC) or to both national classification and IPC		
<b>B. FIELDS SEARCHED</b> Minimum documentation searched (classification system followed by classification symbols) Int.Cl <sup>7</sup> C08L1/00-101/16, C08F20/28, C08F220/28, C08F2/38, C08F4/34 Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched Electronic data base consulted during the international search (name of data base and, where practicable, search terms used) WPI/L		
<b>C. DOCUMENTS CONSIDERED TO BE RELEVANT</b>		
Category*	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	EP, 423998, A (SANYO CHEM IND LTD), 24 April, 1991 (24.04.91), Claims & JP, 03-126702, A Claims	1-8
A	JP, 55-62950, A (Kanegafuchi Chem. Ind. Co., Ltd.), 12 May, 1980 (12.05.80), Claims (Family: none)	1-8
A	JP, 1-245004, A (Kyowa Gas Chemical Ind. Co., Ltd.), 29 September, 1989 (29.09.89), Claims (Family: none)	1-8
A	JP, 7-90029, A (Mitsui Toatsu Chemicals Inc.), 04 April, 1995 (04.04.95), Claims (Family: none)	1-8
A	JP, 7-314615, A (Mitsubishi Rayon Co., Ltd.), 05 December, 1995 (05.12.95), Claims (Family: none)	1-8
<input type="checkbox"/> Further documents are listed in the continuation of Box C. <input type="checkbox"/> See patent family annex.		
* Special categories of cited documents: "A" document defining the general state of the art which is not considered to be of particular relevance "E" earlier document but published on or after the international filing date "L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified) "O" document referring to an oral disclosure, use, exhibition or other means "P" document published prior to the international filing date but later than the priority date claimed "T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention "X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone "Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art "&" document member of the same patent family		
Date of the actual completion of the international search 30 May, 2000 (30.05.00)		Date of mailing of the international search report 06 June, 2000 (06.06.00)
Name and mailing address of the ISA/ Japanese Patent Office		Authorized officer
Facsimile No.		Telephone No.

Form PCT/ISA/210 (second sheet) (July 1992)

**This Page is Inserted by IFW Indexing and Scanning  
Operations and is not part of the Official Record**

**BEST AVAILABLE IMAGES**

Defective images within this document are accurate representations of the original documents submitted by the applicant.

Defects in the images include but are not limited to the items checked:

- ☐ BLACK BORDERS
- ☐ IMAGE CUT OFF AT TOP, BOTTOM OR SIDES
- ☒ FADED TEXT OR DRAWING
- ☐ BLURRED OR ILLEGIBLE TEXT OR DRAWING
- ☐ SKEWED/SLANTED IMAGES
- ☐ COLOR OR BLACK AND WHITE PHOTOGRAPHS
- ☐ GRAY SCALE DOCUMENTS
- ☒ LINES OR MARKS ON ORIGINAL DOCUMENT
- ☐ REFERENCE(S) OR EXHIBIT(S) SUBMITTED ARE POOR QUALITY
- ☐ OTHER: \_\_\_\_\_

**IMAGES ARE BEST AVAILABLE COPY.**

**As rescanning these documents will not correct the image problems checked, please do not report these problems to the IFW Image Problem Mailbox.**